

Test report

T-26385384-10-R1



Verify Report


Overall result

Pass

Please refer to the following pages for test result summary and notes.

Client information

Client: Polyconcept GBS
Address: Zhongshan Wanbo International Center,
Room 301-303, No.666 West Huaihai Road,
Changning District, Shanghai, 200052, China



Sample information

Description: Easy-Read 10 ft. Tape Measure	Purchase order number: 01006901 1 1
Article no.: 1401-80BKYW	Toy Co./agency: -
Factory no: 14395	Labeled age grade: -
Vendor no.: 10167	Requested age grade: -
Country of origin: China	Tested age grade: -
Country of distribution: Canada, United States	
Quantity submitted: 3 pcs + a lot parts	

General information

Sample receipt date: 10-Jun-2026

Report date: 16-Jun-2026

Testing period: 11-Jun-2026 to 16-Jun-2026

QIMA (Hangzhou) Testing Co., Ltd

Jeremy Xu
Chemical Lab Manager

QIMA (Hangzhou) Testing Co., Ltd

Allen Wang
Physical Laboratory Supervisor



Verify Report



Result summary

At the request of the client, the following test were conducted:

Test(s) conducted	Conclusion
California Proposition 65, BPA Migration from Reasonably Accessible Materials	Pass
California Proposition 65, Total Lead in Substrate Materials	Pass
California Proposition 65, Total Lead in Paints and Surface Coatings	Pass
Client's Requirement, Phthalates Content	Pass
16 CFR 1500.3(c)(6)(vi), Flammability of Solids	Pass
19 CFR 134.11-Country of Origin-Labeling Review	Pass



Verify Report



Detailed results

California Proposition 65, BPA Migration from Reasonably Accessible Materials

Test Method: NIOSH Method 9100
Analytical Method: Liquid Chromatography-Tandem Mass Spectrometry (LC-MS/MS)

Specimen No.		C15	---	---	---	Limit	Unit
Test Item	CAS No.	Result	Result	Result	Result		
Bisphenol A (BPA)	80-05-7	ND	---	---	---	3.0	µg/article
Conclusion		Pass	---	---	---		

Note:

µg/article = Micrograms per article

LT = Less than

ND = Not detected (Reporting Limit = 0.5 µg/article)



Verify Report



Detailed results

California Proposition 65, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal);
CPSC-CH-E1002-08.3 (Non-Metal)
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry (ICP-OES)

Specimen No.		C1+C4	C2+C3	C5	C6	Limit	Unit
Test Item	CAS No.	Result	Result	Result	Result		
Lead (Pb)	7439-92-1	ND	ND	ND	ND	100	ppm
Conclusion		Pass	Pass	Pass	Pass		

Specimen No.		C9	C10	C14	---	Limit	Unit
Test Item	CAS No.	Result	Result	Result	Result		
Lead (Pb)	7439-92-1	ND	ND	ND	---	100	ppm
Conclusion		Pass	Pass	Pass	---		

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 10 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.



Verify Report



Detailed results

California Proposition 65, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E1003-09.1 (Coating)
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry (ICP-OES)

Specimen No.		C7+C8	C11+C12+C13	---	---	Limit	Unit
Test Item	CAS No.	Result	Result	Result	Result		
Lead (Pb)	7439-92-1	ND	ND	---	---	90	ppm
Conclusion		Pass	Pass	---	---		

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 10 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.



Verify Report



Detailed results

Client's Requirement, Phthalates Content

Test Method: CPSC-CH-C1001-09.4
Analytical Method: Gas Chromatography-Mass Spectrometry (GC-MS)

Specimen No.		C1+C4	C2+C3	C7+C8	C11+C12+C13	Limit	Unit
Test Item	CAS No.	Result	Result	Result	Result		
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	0.1	% w/w
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	0.1	% w/w
Di-2-ethylhexyl phthalate (DEHP)	117-81-7	ND	ND	0.0071	0.0063	0.1	% w/w
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	0.1	% w/w
Diisononyl phthalate (DINP)	28553-12-0 / 68515-48-0	ND	ND	ND	ND	0.1	% w/w
Diisodecyl phthalate (DIDP)	26761-40-0 / 68515-49-1	ND	ND	ND	ND	0.1	% w/w
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	ND	ND	0.1	% w/w
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	0.1	% w/w
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	0.1	% w/w
Dipentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	0.1	% w/w
Conclusion		Pass	Pass	Pass	Pass		

Note:

% w/w = Percent by weight

LT = Less than

ND = Not detected (Reporting Limit = 0.005 % w/w)

Composite results are based on specimen of least mass resulting in highest potential concentration.



Verify Report



Detailed results

Client's Requirement, Phthalates Content

Test Method: CPSC-CH-C1001-09.4
Analytical Method: Gas Chromatography-Mass Spectrometry (GC-MS)

Specimen No.		C14	---	---	---	Limit	Unit
Test Item	CAS No.	Result	Result	Result	Result		
Dibutyl phthalate (DBP)	84-74-2	ND	---	---	---	0.1	% w/w
Benzyl butyl phthalate (BBP)	85-68-7	ND	---	---	---	0.1	% w/w
Di-2-ethylhexyl phthalate (DEHP)	117-81-7	ND	---	---	---	0.1	% w/w
Diisobutyl phthalate (DIBP)	84-69-5	ND	---	---	---	0.1	% w/w
Diisononyl phthalate (DINP)	28553-12-0 / 68515-48-0	ND	---	---	---	0.1	% w/w
Diisodecyl phthalate (DIDP)	26761-40-0 / 68515-49-1	ND	---	---	---	0.1	% w/w
Di-n-octyl phthalate (DnOP)	117-84-0	ND	---	---	---	0.1	% w/w
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	---	---	---	0.1	% w/w
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	---	---	---	0.1	% w/w
Dipentyl phthalate (DPENP)	131-18-0	ND	---	---	---	0.1	% w/w
Conclusion		Pass	---	---	---		

Note:

% w/w = Percent by weight

LT = Less than

ND = Not detected (Reporting Limit = 0.005 % w/w)



Verify Report



Detailed results

16 CFR 1500.3(c)(6)(vi), Flammability of Solids

Test Method: 16 CFR 1500.44

Test Item	Observation	Conclusion
Flammability of Solids	No Ignition. The content is not defined as flammable solid according to 16 CFR 1500.3(c)(6)(vi).	Pass



Verify Report



Detailed results

19 CFR 134.11-Country of Origin-Labeling Review

Test Method: 19 CFR 134.11

Test Item	Observation	Conclusion
Country of origin	Present on product and can be read easily by consumer at the point of sale.	Pass



Verify Report



Specimen description


Specimen #	Specimen description	Location
C1	Black soft plastic	Shell
C2	Orange plastic	Shell
C3	Black plastic	Shell middle
C4	Black soft plastic	Switch
C5	Silvery metal	Clip
C6	Silvery metal	Tape tail
C7	Black coating	Clip/tape tail
C8	Red ink	Raw material-shell lettering
C9	Silvery metal	Rivet of tape tail
C10	Silvery metal	Tape
C11	Multi-color coating	Tape
C12	Black ink	Raw material-tape
C13	Red ink	Raw material-tape
C14	Transparent plastic	Window
C15	Easy-Read 10 ft. Tape Measure	Finished product





Pictures

Sample photo:



Verify Report



Pictures

Product reference photo:



16x8mm

Item 1401-80BKYW
PO 01006901
China

The photo was provided by the client.

End of the report

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and the method /regulation section(s) tested as described herein. If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule. (<https://www.qima.com/conditions-of-service#decisionRule>). This test report may not be reproduced in whole or in part, without the written approval of QIMA (Hangzhou) Testing Co., Ltd.



Verify Report