

Date: August 30,2021 Page 1 of 2 **Test Report** SL52115297381401TX

CHANGZHOU NEWWIDE KNITTING & DYEING CO., LTD UNIT 9 NO.159 TIANZHOU ROAD, SHANGHAI

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description (A)Knitted fabric

Buyer Polyconcept-Trimark

Sample Color (A)BLACK

Composition (A)65%BCI COTTON 35%RECYCLE POLY

End Use (A)GARMENT

Style No. 18144-98144-18223-98223-18221-98221

Order No. FS2108162 Supplier **NEWWIDE** Country of Destination Canada

Proposed Care Instruction:



Close all fastenings, machine wash cold inside out with like colors, gentle cycle, do not use fabric softener, do not bleach, tumble dry inside out at low temperature, low iron if necessary, do not iron decoration, do not dry clean

Sample Receiving Date Aug 27, 2021

Testing Period Aug 27, 2021 - Aug 30, 2021

Test Result(s) Unless otherwise stated the results shown in this test report refer only to the

sample(s) tested, for further details, please refer to the following page(s).

Test Performed Selected test(s) as requested by applicant

Remark Conclusion Dimensional Stability To Washing FAIL (A)See result

Remark(s): FAIL=Below Client's Requirement

Signed for and on behalf of

SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd Testing Center

Eric Chen (Account Executive)



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3rd Building, No. 889, Yishan Road, Xuhui District Shanghai, China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233

t (86-21) 61402666 t (86-21) 61402666 f (86-21) 64958763 e sgs.china@sgs.com



Test Report Test Result

SL52115297381401TX

Date: August 30,2021

Page 2 of 2

Dimensional Stability To Washing

(AATCC TM 135-2018t; Option 1, Machine wash at 80±5°F with 1.8 kg total loading (Type 1 ballast + specimen) and 66±1g of 1993 AATCC Standard Reference Detergent, Delicate cycle, Tumble Dry Delicate, close all fastenings, wash inside out, do not use fabric softener, tumble dry inside out, do not iron decoration)

After 5 Washes

-	Unit	Α	Requirement
Lengthwise	%	-4.8	+/-3%
Widthwise	%	-2.9	+/-3%

Remark: (+)Means Growth; (-)Means Shrinkage





The statement of conformity in this test report is only based on measured values by the laboratory and does not take their uncertainties into consideration.

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3rd Building, No. 889, Yishan Road, Xuhui District Shanghai, China 200233 中国·上海·徐汇区宜山路889号3号楼 邮编: 200233

t (86-21) 61402666 f (86-21) 64958763 t (86-21) 61402666 f (86-21) 64958763 e sgs.china@sgs.com