

SH

Report Number: EFW525074292-CG-01

Test Result Summary

Test Requested	Result
California Proposition 65 Total Lead Content in Surface Coatings and Substrates	PASS
FDA CPG Sec. 545.400 & 545.450 - Food Contact Materials - Leachable Lead (Pb) and Cadmium (Cd) in Ceramic (Interior)	PASS
California Proposition 65, Leachable Lead and Cadmium in Tableware – Interior	PASS
SOR/2016-175 - Glazed Ceramics and Glassware Regulations - Leachable Lead (Pb) and Cadmium (Cd) (Interior)	PASS
19 CFR 134.11 Country of Origin Markings	PASS
Thermal Shock	PASS

COMPONENT BREAKDOWN LIST:

Test Item	Component Description
A	Santos 12oz Ceramic Mug
A1	Black/brown ceramic(mug) (SM-6355BK)
A2	White/brown ceramic(mug) (SM-6355WH)

TEST RESULT:

California Proposition 65 Total Lead Content in Surface Coatings and Substrates

Test Item	Classification	Total Lead (Pb) (mg/kg)		Conclusion
		Result	Maximum Permissible Limit	
A1	Substrate	44	100	PASS
A2	Substrate	42	100	PASS

Method:

- Lead in other non-metal materials including plastics, glass and leather material:
The test is conducted according to the US CPSC Standard Operating Procedure for Determining Total Lead (Pb) in Non-Metal Children's Products, November 15, 2012 (CPSC-CH-E1002-08.3)

Note: mg/kg = milligram per kilogram
“<” = less than

TEST RESULT:

FDA CPG Sec. 545.400 & 545.450 - Food Contact Materials - Leachable Lead (Pb) and Cadmium (Cd) in Ceramic (Interior)

Test Item	Internal Depth (mm)	Unit	Leaching Volume (mL)	Result (mg/L)	
				Lead	Cadmium
A1	75	(1)	380	<0.05	<0.01
		(2)	380	<0.05	<0.01
		(3)	380	<0.05	<0.01
		(4)	380	<0.05	<0.01
		(5)	380	<0.05	<0.01
		(6)	380	<0.05	<0.01
		Average	380	<0.05	<0.01
Limit (For Cups & Mugs – Any 1 of 6 units)				0.5	0.5
Conclusion				PASS	
Test Item	Internal Depth (mm)	Unit	Leaching Volume (mL)	Result (mg/L)	
				Lead	Cadmium
A2	75	(1)	380	<0.05	<0.01
		(2)	380	<0.05	<0.01
		(3)	380	<0.05	<0.01
		(4)	380	<0.05	<0.01
		(5)	380	<0.05	<0.01
		(6)	380	<0.05	<0.01
		Average	380	<0.05	<0.01
Limit (For Cups & Mugs – Any 1 of 6 units)				0.5	0.5
Conclusion				PASS	

Method: ASTM C738-94 (Reapproved 2020). The lead and cadmium contents are determined by Atomic Absorption Spectrophotometer / Inductively Coupled Argon Plasma Spectrometer / Inductively Coupled Plasma Mass Spectrometer.

The Definition of Food Contact materials are:

- Flatware - Ceramic articles have an internal depth not exceeding 25 mm, measured vertically from the lowest interior point to a horizontal plane passing through the upper rim or the point of overflow.
- Hollow ware - Ceramic articles have an internal depth greater than 25 mm, measured vertically from the lowest interior point to a horizontal plane passing through the upper rim or the point of overflow.
 - Small hollow ware - A capacity of less than 1.1 liter
 - Large hollow ware - A capacity of 1.1 liter or more

Report Number: EFW525074292-CG-01

- c) Cups and mugs - Small ceramic hollow ware vessels commonly used for consumption of beverages, for example, coffee or tea at above room temperature. Cups and mugs normally, but not exclusively, have a capacity of about 240 ml or 8 fl. oz. and are manufactured with a handle. Cups normally have a base and curved sides while a mug has cylindrical sides.
- d) Pitchers - Large ceramic hollow ware vessels (sometimes known as jugs) commonly used for the storing and dispensing of fruit and vegetable juices or other acidic beverages at or below room temperature which are normally manufactured without a lid but with a handle and lip spout.

Note: mL = milliliter
mg/L = milligrams per liter
“<” = less than

TEST RESULT:

California Proposition 65, Leachable Lead and Cadmium in Tableware – Interior

Test Item	Unit	Internal Depth (mm)	Internal Volume (mL)	Leaching Volume (mL)	Concentration relative to Internal Volume (mg/L)	
					Lead	Cadmium
A1	(1)	75	380	380	<0.05	<0.01
	(2)	75	380	380	<0.05	<0.01
	(3)	75	380	380	<0.05	<0.01
	(4)	75	380	380	<0.05	<0.01
	(5)	75	380	380	<0.05	<0.01
	(6)	75	380	380	<0.05	<0.01
	(7)	75	380	380	<0.05	<0.01
	(8)	75	380	380	<0.05	<0.01
	(9)	75	380	380	<0.05	<0.01
	(10)	75	380	380	<0.05	<0.01
	(11)	75	380	380	<0.05	<0.01
	(12)	75	380	380	<0.05	<0.01
Conclusion					PASS (See Remark)	
Test Item	Unit	Internal Depth (mm)	Internal Volume (mL)	Leaching Volume (mL)	Concentration relative to Internal Volume (mg/L)	
					Lead	Cadmium
A2	(1)	75	380	380	<0.05	<0.01
	(2)	75	380	380	<0.05	<0.01
	(3)	75	380	380	<0.05	<0.01
	(4)	75	380	380	<0.05	<0.01
	(5)	75	380	380	<0.05	<0.01
	(6)	75	380	380	<0.05	<0.01
	(7)	75	380	380	<0.05	<0.01
	(8)	75	380	380	<0.05	<0.01
	(9)	75	380	380	<0.05	<0.01
	(10)	75	380	380	<0.05	<0.01
	(11)	75	380	380	<0.05	<0.01
	(12)	75	380	380	<0.05	<0.01
Conclusion					PASS (See Remark)	

Method: ASTM C738-94 (Reapproved 2020). The lead and cadmium contents are determined by Inductively Coupled

Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd

No. 105 Guangzhong Rd., Zhuangqiao Town, Minhang, Shanghai, China P.R.C.201108
Tel: (86) 21-23509600 Fax: (86) 21-23509700

Report Number: EFW525074292-CG-01

Argon Plasma Spectrometer / Atomic Absorption Spectrophotometer / Inductively Coupled Plasma Mass Spectrometer.

Remark: Proposition 65 requires businesses to warn Californians about exposures to certain listed chemicals known to cause cancer, birth defects, or other reproductive harm. If a business exposes a Californian to a listed chemical without providing a warning, then the business may be sued for the possible violation of Proposition 65. The business will then have the burden of proving that the listed chemical in the product is under the safe harbor limit or that the anticipated exposure level will not pose a significant risk of cancer or reproductive harm.

The reformulation levels set forth in the Consent Decrees of similar products to the Sample are

For Lead (Pb):

0.226 mg/L for Flatware and 0.1 mg/L for Hollowware.

For Cadmium (Cd):

1.853 mg/L for Flatware, 0.189 mg/L for Small Hollowware and 0.049 mg/L for Large Hollowware.

The reformulation levels set forth in the various Consent Decrees are only the binding requirements for the defendants named in the case, and by complying with the reformulation requirements, the defendants are protected from further Proposition 65 violations for the products that are covered in the case. However, the reformulation levels set forth in the various Consent Decrees are not necessarily the safe harbor limits. The reformulation levels set in the Consent Decrees are usually expressed in relative concentration levels (i.e., mg/kg, ppm) while the safe harbor limits identify a level of exposure to a listed chemical in micrograms per day. Therefore, for businesses that are not named in the Consent Decrees as defendants, complying with the reformulation levels of Consent Decrees does not fully protect the businesses from being sued for the possible violation of Proposition 65. These businesses may still be sued for the possible violation of Proposition 65 and will have the burden of proving that the listed chemical in their products are under the safe harbor level or that the anticipated exposure level will not pose a significant risk of cancer or reproductive harm.

If your product contains any amount of a listed chemical, the only way to fully avoid the possibility of the burden of proving that the listed chemical in your product is under the safe harbor limit or that the anticipated exposure level will not pose a significant risk of cancer or reproductive harm is to provide a warning about the exposures to the listed chemical known to cause cancer, birth defects, or other reproductive harm. Please consult MTS for more details regarding the different options of labeling and the mechanics of labeling.

The Definition of Food Contact materials are:

- b. Flatware - Ceramic articles have an internal depth not exceeding 25 mm, measured vertically from the lowest interior point to a horizontal plane passing through the upper rim or the point of overflow.
- c. Hollow ware - Ceramic articles have an internal depth greater than 25 mm, measured vertically from the lowest interior point to a horizontal plane passing through the upper rim or the point of overflow.
 - i. Small hollow ware - A capacity of less than 1.1 liter
 - ii. Large hollow ware - A capacity of 1.1 liter or more

Note: mL = milliliter
mm = millimeter
mg/L = milligram per liter
“<” = less than

TEST RESULT:
SOR/2016-175 - Glazed Ceramics and Glassware Regulations - Leachable Lead (Pb) and Cadmium (Cd) (Interior)

Test Item	Internal Depth (mm)	Unit	Leaching Volume (mL)	Result (mg/L)	
				Lead	Cadmium
A1	75	(1)	380	<0.05	<0.01
		(2)	380	<0.05	<0.01
		(3)	380	<0.05	<0.01
		(4)	380	<0.05	<0.01
		(5)	380	<0.05	<0.01
		(6)	380	<0.05	<0.01
		Average	380	<0.05	<0.01
Conclusion				PASS	
Test Item	Internal Depth (mm)	Unit	Leaching Volume (mL)	Result (mg/L)	
				Lead	Cadmium
A2	75	(1)	380	<0.05	<0.01
		(2)	380	<0.05	<0.01
		(3)	380	<0.05	<0.01
		(4)	380	<0.05	<0.01
		(5)	380	<0.05	<0.01
		(6)	380	<0.05	<0.01
		Average	380	<0.05	<0.01
Conclusion				PASS	

Requirement:

Category	Leachability Limit (mg/L)	
	Lead	Cadmium
Flatware	3.0	0.5
Small hollowware, other than cups or mugs	2.0	0.5
Large hollowware, other than pitchers	1.0	0.25
Cups & Mugs	0.5	0.5
Pitchers	0.5	0.25

Method: ISO 6486-1:2019, Ceramic ware, glass-ceramic ware and glass dinnerware in contact with food — Release of lead and cadmium — Part 1: Test Method, second edition, 1999-12-15. The lead and cadmium contents are determined by Atomic Absorption Spectrophotometer / Inductively Coupled Argon Plasma Spectrometer / Inductively Coupled Plasma Mass Spectrometer.

Note: mL = milliliter
mg/L = milligrams per liter
“<” = less than

Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd

No. 105 Guangzhong Rd., Zhuanqiao Town, Minhang, Shanghai, China P.R.C.201108
Tel: (86) 21-23509600 Fax: (86) 21-23509700

Report Number: EFW525074292-CG-01

TEST RESULT:

Test Property	Method	Applicable Components	Limits	Notes	Result
19 CFR 134.11 Country of Origin Markings	Not Applicable	Per Review	Not Applicable	Products Manufactured outside of USA.	PASS
Thermal Shock	ASTM C149-86- Modified	Per Glass/Ceramic product	Product shall not crack or shatter after being subjected to extreme temperature change: Ceramic mugs & dinnerware: 212°F to 68°F Glass kitchenware & dinnerware: 145°F to 70°F Glass Drinkware: 212°F to 68°F	--	PASS

Photo of Exhibit


Report Number: EFW525074292-CG-01

*****End of Test Report*****

NOTE:If there is question or concern regarding the above results, please contact us via email coco.yu@cpt.eurofinscn.com

This test report is governed by the Terms and Conditions, available on request or accessible at <https://www.eurofins.cn/consumer-product-testing/general-terms/>. Attention is especially drawn to the limitations of liability, indemnification and jurisdictional provisions defined therein. This report is issued strictly based on the testing of the samples submitted by you. The test results in this report refer only to the sample(s) actually tested and do not refer or be deemed to refer to any bulk production from which such sample(s) may be said to have been obtained. In the event that Eurofins MTS Consumer Product Testing (Shanghai) Co., Ltd. ("ERF") was requested to survey and test any bulk production quantity of samples, ERF, in the absence of any contrary written instructions, performed random sampling of bulk production for testing purposes. Variations in the conditions under which samples are stored, transported, etc., may lead to variations in the test results. ERF cannot anticipate and shall not be held responsible for variations in test results that may be due to factors beyond ERF's control, such as, sample cross-contamination, evaporation of volatile substances due to storage temperature, humidity, etc. This report does not constitute a recommendation, actual or implied, for any specific course of action. Other than the expressed warranties made in the Terms and Conditions of the ERF Test Request Form, ERF makes no warranties or representations either express or implied with respect to this report. In no circumstances whatsoever shall ERF be liable for any consequential, special or incidental damages arising out of, or in connection with, this report. This document shall not be reproduced except in full unless prior written authorization from ERF has been attained. Unless otherwise stated from the customer, regulation or the standard specification, Eurofins will apply it in accordance with ILAC G8:09/2019 (binary statement for simple acceptance rule) and shared risk decision rule. If you happen to have any complaints, please do it by sending email to info.shmts@cpt.eurofinscn.com and referring to this report number.