

LAB LOCATION: DONG GUAN **REPORT NUMBER:** 63123-110340 Addendum 1
DATE IN: November 10, 2023 **DATE OUT:** November 20, 2023
ADDENDUM DATE: November 21, 2023

Applicant:	Polyconcept GBS		
Contact:	Kathy Lu		
Address:	4th Floor, Hongqiao Rongguang Building, 11 Changshun Road, Changning District, Shanghai, 200051, PRC		
TEL:	13918486858	FAX:	--
E-mail:	testprogram@pcna.com ; kathy.lu@polyconceptgbs.com ; claire.li@polyconceptgbs.com ; kkolber@pcna.com ;		
Copy To:	--		

<u>OVERALL RATING</u>	
SATISFACTORY	<u>X</u>
UNSATISFACTORY	<u>--</u>

Sample Information

	Sample Description:	5.5"x8.5" Mano Recycled Hard Bound JournalBook 5.5"x8.5" Skiva Soft Bound JournalBook
	PO Number:	2045578/2045575/2045574/2045579 /2045581/2045582
	Article Number:	2900-48BK/GY/NY/2900-49BK/GY/NY
	Number of Sample Submitted:	3pcs/SKU, 18pcs in all
	Factory Number:	12757
	Vendor Number:	11506
	Customer:	Leeds
	Country of Origin:	China
	Country of Destination:	US/CAN
	Retest – Previous Report No:	/
Remark: /		

Test Result Summary	
CONCLUSION	TEST(S) CONDUCTED
PASS	California Proposition 65 Total Lead Content in Substrates
PASS	Phthalate Content (10P)
PASS	19 CFR 134.11 Country of Origin Markings
Information only	16 CFR 24-Leather-Guides for Select Leather and Imitation Leather Products-labeling

For and on behalf of
Modern Testing Services (Dongguan) Limited



Li Xin Yu, Insoul
Assistant Manager, Hardlines

COMPONENT BREAKDOWN LIST:

Test Item	Component Description
A	Mano Recycled Hard Bound Journal Book (2900-48NY)
B	Mano Recycled Hard Bound Journal Book (2900-49NY)
C	Mano Recycled Hard Bound Journal Book (2900-48GY)
D	Mano Recycled Hard Bound Journal Book (2900-49GY)
E	Mano Recycled Hard Bound Journal Book (2900-48BK)
F	Mano Recycled Hard Bound Journal Book (2900-49BK)
1	Black plastic with navy fabric wrapping (Elastic on cover) (2900-48NY / 2900-49NY) (A / B)
2	Black plastic with navy fabric wrapping (Elastic loop) (2900-48NY / 2900-49NY) (A / B)
3	Black plastic with grey fabric wrapping (Elastic on cover) (2900-48GY / 2900-49GY) (C / D)
4	Black plastic with grey fabric wrapping (Elastic loop) (2900-48GY / 2900-49GY) (C / D)
5	Black plastic with black fabric wrapping (Elastic on cover) (2900-48BK / 2900-49BK) (E / F)
6	Black plastic with black fabric wrapping (Elastic loop) (2900-48BK / 2900-49BK) (E / F)
7	Navy plastic with navy fabric backing and grey / beige paper backing and adhesive (Cover) (2900-48NY / 2900-49NY) (A / B)
8	Grey plastic with grey fabric backing and grey / beige paper backing and adhesive (Cover) (2900-48GY / 2900-49GY) (C / D)
9	Black plastic with black fabric backing and grey / beige paper backing and adhesive (Cover) (2900-48BK / 2900-49BK) (E / F)
10	Navy fabric (Rope) (2900-48NY / 2900-49NY) (A / B)
11	Grey fabric (Rope) (2900-48GY / 2900-49GY) (C / D)
12	Black fabric (Rope) (2900-48BK / 2900-49BK) (E / F)
13	Beige paper with black printing (Page) (2900-48NY / 2900-49NY / 2900-48GY / 2900-49GY / 2900-48BK / 2900-49BK) (A / B / C / D / E / F)

TEST RESULT:

1. Total Lead Content – Client’s Requirement according to the Consent Decrees of California Proposition 65

Test Item	Classification	Total Lead (Pb) (mg/kg)		Conclusion
		Result	Client’s Limit	
1+2+3	Accessible substrate	<10	100	PASS
4+5+6	Accessible substrate	<10	100	PASS
7+8+9	Accessible substrate	<10	100	PASS
10+11+12	Accessible substrate	<10	100	PASS
13	Accessible substrate	<10	100	PASS

Method: Sample was digested with acid mixture and analyzed by Atomic Absorption Spectrophotometer / Inductively Coupled Argon Plasma Spectrometer / Inductively Coupled Plasma Mass Spectrometer.

Note: mg/kg = milligram per kilogram
“<” = less than

2. Phthalates Content- Client's Requirement

Test Item	Phthalates Content (%)		Conclusion
	Result	Client's requirement	
1+2+3	<0.005 (individual)	0.1 (individual)	PASS
4+5+6	<0.005 (individual)	0.1 (individual)	PASS
7+8+9	<0.005 (individual)	0.1 (individual)	PASS

List of Phthalates:

Chemical Name	CAS No.	Chemical Name	CAS No.
Dibutyl phthalate (DBP)	84-74-2	Di-iso-decyl phthalate (DIDP)	26761-40-0/ 68515-49-1
Butyl benzyl phthalate (BBP)	85-68-7	Di-iso-nonyl phthalate (DINP)	28553-12-0/ 68515-48-0
Di-2-ethylhexyl phthalate (DEHP) / Diocetyl phthalate (DOP)	117-81-7	Di-n-octyl phthalate (DNOP)	117-84-0
Di-iso-butyl phthalate (DIBP)	84-69-5	Dipentyl phthalate (DPP / DPENP)	131-18-0
Di-n-hexyl phthalate (DNHP/ DHEXP)	84-75-3	Dicyclohexyl phthalate (DCHP)	84-61-7

Method: Sample was extracted with organic solvent and analyzed by Gas Chromatograph Mass Spectrometer / Liquid Chromatograph Mass Spectrometer.

Note: % = percentage
" < " = less than

3. Labeling Review - 19 CFR 134.11 Country of Origin Markings


Result: PASS (Made in China)

Applicable Components: Per Review

Notes: Products Manufactured outside of USA

4. 16 CFR 24-Leather-Guides for Select Leather and Imitation Leather Products-labeling

Test / Regulation	Observation	Conclusion
16 CFR 24-Leather-Guides for Select Leather and Imitation Leather Products	No labeling is provided. Labeling "imitation leather" or "simulated leather" should be provided if the sample is not made of genuine leather.	Information only

EXHIBIT:**Remark:**

This is the addendum report of 63123-110340, the label review of Leather-Guides for Select Leather and Imitation Leather Products was added into this report.

NOTE:

If there is question or concern regarding the above results, please contact the appropriate lab person below:

Contact: Yan Lie Fei, Lemon TEL: (86)769 8112 0818 Ext.875 Email: Lemon.Yan@cpt.eurofinscn.com

This test report is governed by the Terms and Conditions, available on request or attached to the end of this test report. Attention is especially drawn to the limitations of liability, indemnification and jurisdictional provisions defined therein. This report is issued strictly based on the testing of the samples submitted by you. The test results in this report refer only to the sample(s) actually tested and do not refer or be deemed to refer to any bulk production from which such sample(s) may be said to have been obtained. In the event that Modern Testing Services (Dongguan) Limited ("ERF") was requested to survey and test any bulk production quantity of samples, ERF, in the absence of any contrary written instructions, performed random sampling of bulk production for testing purposes. Variations in the conditions under which samples are stored, transported, etc., may lead to variations in the test results. ERF cannot anticipate and shall not be held responsible for variations in test results that may be due to factors beyond ERF's control, such as, sample cross-contamination, evaporation of volatile substances due to storage temperature, humidity, etc. This report does not constitute a recommendation, actual or implied, for any specific course of action. Other than the expressed warranties made in the Terms and Conditions of the ERF Test Request Form, ERF makes no warranties or representations either express or implied with respect to this report. In no circumstances whatsoever shall ERF be liable for any consequential, special or incidental damages arising out of, or in connection with this report.